

# TECHNICAL DATA SHEET



## WET-LOOK SEALER

QP-1470

<b>PRODUCT DESCRIPTION</b>	<p><b>Wet-Look Nano-Ceramic Clear Water Proofing.</b>  <b>QproTECH Wet-Look Sealer QP-1470:</b></p> <ul style="list-style-type: none"> <li>• is a single component solution, ambient cures and has extreme hydrophobic properties.</li> <li>• creates a hydrophobic barrier on pavers, brick, concrete, aggregate and natural stone.</li> <li>• creates an intrinsic bond to the substrate material penetrating deep into substructure.</li> <li>• will reduce deterioration caused by water absorption such as, spalling, cracking, pitting, staining and salt absorption, as well as the formation of mold and mildew.</li> </ul>			
<b>SUGGESTED USES</b>	<p><b>QproTECH Wet-Look Sealer</b> is perfect for driveways, walkways, stairs, pool decks and patios, garage floors, retail, restaurant and warehouse floors and walls, basement floors and walls and more.</p>			
<b>PROPERTIES</b>	<b>Colour</b>	Clear	<b>Estimated Coverage Rate</b> (porous substrates)	125-175 sq./ft. per gal. *
	<b>% of Solids</b>	40%	<b>Estimated Coverage Rate</b> (dense substrates)	250 sq./ft. per gal. *
	<b>Odor (liquid)</b>	Slight Solvent	<b>Dry to Touch</b> (time @ambient)	1 to 2 hrs ** (average)
	<b>Odor (cured)</b>	None	<b>Re-coat Time</b>	1 to 2 hrs.
	<b>V.O.C.</b>	Low V.O.C.	<b>Foot Traffic</b>	12 to 24 hrs.
	<b>RoHS</b>	Compliant	<b>Wheeled Traffic</b>	24 to 48 hrs.
	<b>REACH</b>	Compliant	<b>Application Temperature</b>	45° to 85°F
	<b>Halogens</b>	None		

(\* absorbency of the solution into the substrate will vary results)  
(\*\* warm ambient temperature may help to reduce the dry time)

The manufacturer is not responsible for the use and application of this material. At the time of this publication all information contained within was determined to be valid and true. It is up to the end user determine the suitability of this product for their own application. No warranty is written or implied regarding application and use of this material.

